

SIVIT SRL

Via Centallo, 57

10156 TORINO - ITALY

Tel. 0039 011 2730033 - Fax 0039 011 2735617

www.sivit.it

info@sivit.it

Rev. A del 11/05 - Sigla

ANTI-DUST PRIMER

- ◆ Concrete surfaces must be solid, dry (new concrete must be seasoned), levelled, absorbent, free from oil, detergents, dust and other substances.
You should consider whether to treat the surface by abrasion or chemical washing.
Very absorbent and non-contaminated surfaces can be treated directly after proper cleaning.
- ◆ The stains of substrate will remain visible after treatment.
- ◆ Apply a coat of waterborne two-pack epoxy system PAVIWATER T/68 A+B , diluted 1 : 3 in water for a consumption of 0,050 kg/m² of A+B.
- ◆ Apply a second coat of PAVIWATER T/68 A+B diluted 1 : 1,5 with water for a consumption of 0,050 Kg/m² of A+B.