

SIVIT SRL

Via Centallo, 57

10156 TORINO - ITALY

Tel. 0039 011 2730033 – Fax 0039 011 2735617

www.sivit.it

info@sivit.it

Rev. A del 11/05 – Sigla

COVERING BASED ON WATERBORNE EPOXY MORTAR
FILLED WITH IRON GRAINS

- ◆ Concrete surfaces must be solid, dry (new concrete must be seasoned), levelled, absorbent, free from oil, detergents, dust and other substances.
You should consider whether to treat the surface by abrasion or shot-peening.
Any holes or slight anomalies can be repaired with PAVIRAPID A+B.

- ◆ Apply a coat of PAVIWATER T/68 A+B diluted 1 : 1,5 with water for a consumption of 0,100 Kg/m².

- ◆ Apply a coat of ECOFER RASATURA A+B+C for a consumption of 1 Kg/m².

- ◆ Apply a second coat of ECOFER RASATURA A+B+C for a consumption of 0,500 Kg/m².

- ◆ Apply a coat of PAVIWATER colorato A+B by roller for a consumption of 0,130 Kg/m².