

**SIVIT SRL**  
Via Centallo, 57  
10156 TORINO - ITALY  
Tel. 0039 011 2730033 – Fax 0039 011 2735617  
[www.sivit.it](http://www.sivit.it)      [info@sivit.it](mailto:info@sivit.it)

Rev. A del 11/05 - Sigla

**PERMEABLE TO MOISTURE RESINOUS COVERING**  
**OF THICKNESS ROUND ABOUT 1 MM**

- ◆ Concrete surfaces must be solid, dry (new concrete must be seasoned), levelled, absorbent, free from oil, detergents, dust and other substances.  
You should consider whether to treat the surface by abrasion or shot-peening.  
Any holes or slight anomalies can be repaired with PAVIRAPID A+B.
  
- ◆ Apply a coat of PAVIWATER T/68 A+B diluted 1:1,5 with water for a consumption of 0,070 Kg/m<sup>2</sup> of A+B.
  
- ◆ Apply a coat of COLORSIVIT MALTA NEUTRO A+B coloured with 10% of COLORPASTA W for a consumption of 0,800 Kg/m<sup>2</sup> of A+B
  
- ◆ Apply a second coat of COLORSIVIT MALTA NEUTRO A+B coloured with 10% of COLORPASTA W for a consumption of 0,800 Kg/m<sup>2</sup> of A+B.
  
- ◆ Top-coating based on waterborne epoxy system PAVIWATER colorato A+B diluted with 10% of water for a consumption of 0,130 Kg/m<sup>2</sup>.