

SIVIT SRL
Via Centallo, 57
10156 TORINO - ITALY
Tel. 0039 011 2730033 – Fax 0039 011 2735617
www.sivit.it info@sivit.it

Rev. A del 11/05 – Sigla

RESINOUS FLOORING FOR FOOD INDUSTRIES
(exclusively for specialized operator)

- ◆ Milling or shot-peening the surface with the aim to eliminate the inconsistency and loose parts.
- ◆ Apply a coat of FLUIDEPOX A+B for a consumption 0,500 Kg/m² then apply the troweling mortar (Quartz MIX1 in combination with epoxy resin in ratio 10 : 1) and compact the mortar with proper tool (with a consumption of 15 Kg/m² of mixture for a thickness of 7-8 mm).
- ◆ Apply a coat of FLUIDEPOX A+B to saturate the porosity for a consumption of 0,500 Kg/m².
- ◆ Apply a coat of PAVIPLAST A+B filled 1 : 0,8 with Quartz B0 for a consumption of 0,900 Kg/m².
- ◆ Apply a coat of FINISOL colorato A+B by roller for a consumption of 0,130 Kg/m².

Rev. A del 11/05 - Sigla

RESINOUS FLOORING FOR FOOD INDUSTRIES

- ◆ When required, cut of covering in relation of joint of concrete and filling with polyurethane elastomeric sealant **SIGILFLEX**.

N.B. This resinous covering has the following properties:

-satisfies the directive 93/43/CEE on the hygiene of Foodstuffs

-washable

-resistant to sudden thermic changes (for example during a washing with steam)

-non-absorbent

-non-toxic