

SIVIT SRL

Via Centallo, 57

10156 TORINO - ITALY

Tel. 0039 011 2730033 – Fax 0039 011 2735617

www.sivit.it

info@sivit.it

Rev. A del 11/05 - Sigla

SELF-LEVELLING COVERING PERMEABLE TO MOISTURE
BASED ON WATERBORNE EPOXY MORTAR

- ◆ Concrete surfaces must be solid, dry (new concrete must be seasoned), levelled, absorbent, free from oil, detergents, dust and other substances.
You should consider whether to treat the surface by abrasion, milling or shot-peening. Any holes or slight anomalies can be repaired with PAVIRAPID A+B.
- ◆ Apply a coat of PAVIWATER T/68 A+B diluted 1 : 1,5 with water for a consumption of 0,100 Kg/m² of A+B.
- ◆ Filling of dilatation joint with ECOPAVIPLAST A+B+C filled with an excess of CARICA ECOPAVIPLAST.
- ◆ If the surface of flooring is irregular it is necessary to make a smoothing with ECOPAVIPLAST A+B+C for a consumption of 1-2 kg/m².
- ◆ Apply self-levelling product by a serrated trowel for a consumption of 5 kg/m² (covering of 3 mm of thickness) then uniform the surface thanks to a spiked roller.

Rev. A del 11/05 - Sigla

**SELF-LEVELLING COVERING PERMEABLE TO
MOISTURE BASED ON WATERBORNE EPOXYMORTAR**

- ◆ Top-coating based on waterborne epoxy system **PAVIWATER A+B** diluted with 10% of water for a consumption of 0,130 Kg/m².
- ◆ When required, cut of covering in relation of joint of concrete and filling with polyurethane elastomeric sealant **SIGILFLEX** or by a pvc packing.