

SIVIT SRL
Via Centallo, 57
10156 TORINO - ITALY
Tel. 0039 011 2730033 - Fax 0039 011 2735617
www.sivit.it info@sivit.it

Rev. A del 11/05 - Sigla

SOLVENTBORNE POLYURETHANE VARNISHING ON CONCRETE SURFACE

- ◆ Concrete surfaces must be solid, dry (new concrete must be seasoned), levelled, absorbent, free from oil, detergents, dust and other substances.
You should consider whether to treat the surface by abrasion or shot-peening.
- ◆ Apply a coat of FINISOL colorato A+B diluted with 10% of SOLVENTE UNI for a consumption of 0,120 kg/m².
- ◆ Apply a second coat of FINISOL colorato A+B for a consumption of 0,120 Kg/m².
FINISOL colorato A+B can be filled with quartz or glass bubbles to obtain a anti-slip surface.