

SIVIT SRL

Via Centallo, 57

10156 TORINO - ITALY

Tel. 0039 011 2730033 – Fax 0039 011 2735617

www.sivit.it

info@sivit.it

Rev. A del 11/05 - Sigla

WATERBORNE EPOXY VARNISHING ON CONCRETE

- ◆ Concrete surfaces must be solid, dry (new concrete must be seasoned), levelled, absorbent, free from oil, detergents, dust and other substances.

You should consider whether to treat the surface by abrasion or shot-peening.

- ◆ Apply a coat of PAVIWATER colorato A+B diluted with 20% of water for a consumption of 0,130 kg/m².

- ◆ Apply a second coat of PAVIWATER colorato A+B diluted with 10% of water for a consumption of 0,130 Kg/m².

PAVIWATER colorato A+B can be filled with quartz or glass bubbles to obtain a anti-slip surface.