



Head Office and Plant:
Via Centallo, 57 - 10156 Turin
Tel. +39-011 273.00.33
Fax +39-011 273.56.17

www.sivit.it
s.r.l. ser.tec@sivit.it

Technical
Sheet

Rev. A del 10/05 ó Cod.80- Sigla

COLORSIVIT 00

Uses

Resinous product for decorative covering, suitable for walls and floors

Description

Waterborne one component product based on acrylic copolymers. Thanks evaporation of water is obtained a covering easy sandable (system is filled with glass bubbles).

The product isn't coloured

Preparation and application :

COLORSIVIT 00 is usually applied on COLORSIVIT M or COLORSIVIT MALTA.
In some cases could be necessary to sand the surface before applying the products.

Application:

- Add to the system COLORPASTA W and mix carefully until to obtained a homogenous system (the amount of waterbased dispersion changed in according to shade desired).
- Apply two coats of product by American trowel.
- To obtain a good decorative effect is necessary to use the following % of COLORPASTA W:
 - 10% for first coat
 - 2% for second coat
- Is necessary to avoid film too thickness that could delay the development of the final characteristic of product, in particular drying in depht (crack of covering)

TECHNICAL FEATURES:

Appearance:	tixotropic paste
Colour:	light grey
Solid content:	32% in weight
Specific Weight:	1,70 +/-0,05 g/ml
Flash point:	not applicable
Tack free time:	20-30' (25°C-50% U.R.)
Overcoat time:	1,5h (25°C-50% U.R.)
Coverage capacity:	0,25 - 0,6 Kg for smoothing in according to roughness of surface.
Application conditions:	Temperature between +7°C and +30°C U.R. < 80%
Solvent to clean the tools:	Water
Storage:	12 months. Keep in a dry place at a temperature between 5°C and 35°C.